



Effective oxidation of alcohols by Iron(III)-Schiff base-triphenylphosphine complexes

Sandya Rani, Badekai Ramachandra Bhat*

Catalysis and Materials Chemistry Division, Department of Chemistry, National Institute of Technology Karnataka, Surathkal, Srinivasanagar 575025, India

ARTICLE INFO

Article history:

Received 13 August 2010

Revised 21 September 2010

Accepted 24 September 2010

Available online 1 October 2010

Keywords:

Fe(III) complex

Schiff base

Hydrogen peroxide

Alcohol oxidation

ABSTRACT

Iron(III)-Schiff base-triphenylphosphine complexes catalyze the oxidation of alcohols to their corresponding carbonyl compounds in presence of hydrogen peroxide in good yields.

© 2010 Elsevier Ltd. All rights reserved.

The transformation of alcohols into aldehydes and ketones is of paramount importance in organic chemistry, both for laboratory scale experiments and in the manufacturing processes. Whereas the oxidation of primary and secondary alcohols into the corresponding aldehydes and ketones is a fundamental reaction in organic synthesis, still many oxidation processes use non-environmentally friendly oxidants.¹ In recent years, there has been an increasing need for search of catalytic oxidations with inexpensive green oxidants, such as molecular oxygen or hydrogen peroxide. Accordingly, several studies have been recently reported for the oxidation of alcohols with molecular oxygen or hydrogen peroxide catalyzed by transition metal salts or complexes of V,² Pd,³ Mo,⁴ Ru,⁵ Co,⁶ Cu,⁷ etc. Though extensive research efforts have been invested in the development of many of these metal catalyzed reactions, there are only a few reports of using cheap and less toxic iron catalysts for the oxidation of alcohols to carbonyls so far.⁸ In particular, iron-catalyzed reactions have several practical advantages over the analogous palladium or nickel-mediated reactions. The low cost and ample supply of iron salts coupled with their environmentally benign nature and lack of toxicity make them ideal for industrial scale synthesis of fine chemicals.

Very recently, we developed an efficient method for the selective oxidation of alcohols to the corresponding aldehydes and ketones using iron(III) complexes [**FeL**₁–**FeL**₄] containing triphenylphosphine and a Schiff base, *N*-(2-mercaptophenyl)salicylideneimine and its derivatives (Fig. 1) as a catalyst using periodic acid at ambient temperature in acetonitrile medium.⁹ As a part of our

ongoing research toward iron-catalyzed oxidation chemistry, herein, we report the catalytic oxidation of benzylic and allylic alcohols to the corresponding carbonyl compounds in good to high yields with iron(III) complexes using H₂O₂ in acetonitrile (Scheme 1). This procedure is very simple, mild, and clean and works efficiently without any additives.

The oxidation of benzylic alcohol, as a standard substrate, was first investigated in order to optimize the reaction variables such as solvent, temperature, alcohol/oxidant molar ratio, and length of the reaction time. We checked first the activity of **FeL**₁ in





Figure 1. General structure of the complexes.




Scheme 1. Conversion of alcohols to carbonyl compounds.

* Corresponding author. Tel.: +91 824 2474000x3204; fax: +91 824 2474033.

E-mail address: chandpoorna@yahoo.com (B.R. Bhat).

Table 1
Optimization of reaction conditions for oxidizing benzyl alcohol to benzaldehyde^a

Entry	Amount of FeL₁ (mmol)	Amount of oxidant (mmol)	Yield ^b (%)
			CH ₃ CN–H ₂ O ₂ system
1	0	5.0	2.4
2	0.01	5.0	22.0
3	0.02	5.0	46.5
4	0.03	5.0	74.4
5	0.04	5.0	80.1
6	0.05	5.0	79.7
7	0.04	0	1.7
8	0.04	1.0	43.3
9	0.04	2.0	60.2
10	0.04	3.0	69.9
11	0.04	4.0	74.6
12	0.04	6.0	79.9

















^a 1 mmol benzyl alcohol, 10 mL CH₃CN, 90 min, 80 °C.^b GC yield, average of three trials.**Figure 2.** Effect of time on the yield of benzyl alcohol to benzaldehyde.**Table 2**
Oxidation of alcohols catalyzed by Fe(III) complexes^a in CH₃CN–H₂O₂ system

Alcohols	Product	Yield of carbonyl compound ^b (%)			
		FeL₁	FeL₂	FeL₃	FeL₄
		80.1	78.4	78.9	79.3
		79.5	77.5	78.2	78.6
		78.3	76.0	77.8	76.8
		82.6	81.2	81.7	82.0

different solvents (methanol, acetonitrile, and acetone) with H₂O₂ as the oxidant. The best conversions have been observed in acetonitrile. The activity of **FeL₁** was studied at different temperature by taking benzyl alcohol as the model substrate in acetonitrile–H₂O₂ system. It was observed that at 80 °C, the system showed higher conversion. The optimization of other reaction conditions was studied by taking benzyl alcohol as substrate with **FeL₁** in acetonitrile–H₂O₂ system (Table 1). In order to study the effect of time on the activity, the product analysis was done at regular intervals of time under similar reaction conditions (Fig. 2). It was observed that the yield remains constant after a reaction time of 90 min. The effect of the concentration of catalyst with respect to substrate was carried out at different substrate to catalyst ratios. A 0.04 mmol of catalyst was sufficient for the effective transformation of benzyl alcohol into benzaldehyde (Table 1, entry 5). The yield was insignificant when the reaction was carried in absence of catalyst (Table 1, entry 1). This observation reveals the catalytic role of iron(III) complexes. The reaction was studied at various substrates to oxidant ratios (Table 1). A minimum quantity of 5 mmol of the oxidant was necessary for the effective oxidation of benzyl alcohol to benzaldehyde (Table 1, entry 5). The catalytic activities of **FeL₂**–**FeL₄** in acetonitrile–H₂O₂ were carried out (Table 2).¹⁰ From the Table 2, it is clear that the **FeL₁** in acetonitrile–H₂O₂ system showed good efficiency. The reported iron complexes in acetonitrile–H₂O₂ system are found to be more efficient compared with the reported work on iron complexes for the oxidation of alcohols to carbonyls.⁸

The oxidation was extended to a variety of alcohols including primary and secondary, aromatic, aliphatic, and cyclic alcohols using the optimized reaction conditions. The results for the oxidation of a variety of alcohols are summarized in Table 2. All the benzylic primary and secondary alcohols were oxidized smoothly to give aldehydes and ketones, respectively. Among the various alcohols studied those containing aromatic substituent were found to be more reactive than alicyclic and aliphatic alcohols. All the reactions occurred with complete selectivity for ketones or aldehydes and no other products were detected in the reaction mixture. The over oxidation to carboxylic acid was ruled out by derivative test.

Table 2 (continued)

Alcohols	Product	Yield of carbonyl compound ^b (%)			
		FeL ₁	FeL ₂	FeL ₃	FeL ₄
		79.7	77.2	76.3	77.8
		75.6	73.8	74.8	75.2
		71.9	70.8	71.4	69.8
		70.5	68.9	69.4	70.1
		36.8	33.6	35.2	36.1
		28.3	26.5	25.0	27.6
		23.1	20.6	22.6	22.9
		22.3	20.5	21.6	22.1

^a 1 mmol alcohol, 5.0 mmol H₂O₂, 0.04 mmol Fe(III) complex, 10 mL CH₃CN, stirring at 80 °C.

^b GC yield, average of three trials.

In conclusion, oxidation of alcohols using hydrogen peroxide, a mild oxidant, in the presence of catalytic amounts of synthesized iron(III) complexes provides a simple, safe, and efficient method for oxidation of aromatic alcohols to corresponding carbonyls with high yield.

References and notes

- (a) Trost, B. M.; Fleming, I. In *Comprehensive Organic Synthesis*; Pergamon Press: UK, 1991. p 7; (b) Corey, E. J.; Barrette, E.-P.; Plato Magriotis, A. *Tetrahedron Lett.* **1985**, 26, 5855; (c) Firouzabadi, H.; Iranpoor, N.; Kueiezadeh, F.; Toofan, J. *Tetrahedron Lett.* **1986**, 42, 719.
- (a) Pawel, J. F.; Jaroslaw Sobczak, M.; Jozef Ziolkowski, J. *Chem. Commun.* **2004**, 244; (b) Lingaiah, N.; Mohan Reddy, K.; Seshu Babu, N.; Narasimha Rao, K.; Suryanarayana, I.; Sai Prasad, P. S. *Catal. Commun.* **2006**, 7, 245.
- (a) Mitchell Schultz, J.; Candice Park, C.; Matthew Sigman, S. *Chem. Commun.* **2002**, 3034; (b) Karimi, B.; Zamani, A. *J. Iran. Chem. Soc.* **2008**, 5, S1–S20.
- (a) Ankush Biradar, V.; Mohan Dongare, K.; Shubhangi Umbarkar, B. *Tetrahedron Lett.* **2009**, 50, 2885; (b) Gharah, N.; Chakraborty, S.; Alok Mukherjee, K.; Bhattacharyya, R. *Inorg. Chim. Acta* **2009**, 362, 1089.
- (a) Nakamura, Y.; Egami, H.; Matsumoto, K.; Uchida, T.; Katsuki, T. *Tetrahedron* **2007**, 63, 6383; (b) Egami, H.; Shimizu, H.; Katsuki, T. *Tetrahedron Lett.* **2005**, 46, 783.
- (a) Vishal Sharma, B.; Suman Jain, L.; Sain, B. *J. Mol. Catal. A: Chem.* **2004**, 212, 55; (b) Das, S.; Punniyamurthy, T. *Tetrahedron Lett.* **2003**, 44, 6033.
- (a) Velusamy, S.; Srinivasan, A.; Punniyamurthy, T. *Tetrahedron Lett.* **2006**, 47, 923; (b) Istva Marko, E.; Paul Giles, R.; Tsukazaki, M.; Stephen Brown, M.; Urch, C. J. *Science* **1996**, 274, 2044.
- (a) Shul'pina, L. S.; Veghini, D.; Kudinov, A. R.; Shulpin, G. B. *React. Kinet. Catal. Lett.* **2006**, 88, 157; (b) Alette Ligtenbarg, G. J.; Oosting, P.; Roelfes, G.; Crois, R. La. M.; Lutz, M.; Anthony Spek, L.; Hage, R.; Feringa, B. L. *Chem. Commun.* **2001**, 385; (c) Klopstra, M.; Hage, R.; Kellogg, R. M.; Feringa, B. L. *Tetrahedron Lett.* **2003**, 44, 4581; (d) Shil, X.-y.; Wei, J.-F. *J. Mol. Catal. A: Chem.* **2005**, 229, 13; (e) Balogh Hergovicha, E.; Speier, G. J. *Mol. Catal. A: Chem.* **2005**, 230, 79.
- Rani, S.; Bhat, R. B. *Inorg. Chem. Commun.*, doi:org/10.1016/j.inoche.2010.07.018.
- Procedure: A solution of the complexes (0.04 mmol) in 10 ml acetonitrile was added to the solution of substrate (1 mmol) and H₂O₂ (5 mmol, 30%). The reaction mixture was stirred at 80 °C for 90 min. The residue was then extracted with a minimal volume of ether and dried over MgSO₄. The ether solution was then analyzed by GC using dichlorobenzene as internal standard.